

## Aduro Vitea

2651

Solvent-based 2C polyurethane matt varnish for furniture and interior finishing, for use in industry and trade

### PRODUCT DESCRIPTION

Product numbers

2651000105

General


Fast-drying 2C polyurethane clear varnish formulated with acrylate resin for retaining the natural look and feel of the wood. Very good chemical and good mechanical resistance, elegant matt effect and attractive pore pattern.

Special properties and standards

- **ÖNORM A 1605-12 (furniture surfaces)**  
Confirmed by an external test certificate.  
Resistance to chemical reactions: 1-B1  
Response to abrasion: 2-D ( $\geq 50$  U)  
Response to scratches: 4-D ( $\geq 1.0$  N)
- **DIN 68861 (furniture surfaces)**  
Confirmed by an external test certificate.  
Part 1: Response to chemical stress: 1 B  
Part 2: Response to Abrasion: 2 D ( $> 50$  to  $\leq 150$  U)  
Part 4: Response to scratches: 4 D ( $> 1,0$  to  $\leq 1,5$  N)
- **ÖNORM A 3800-1 (fire behaviour)**  
In conjunction with a flame-retardant substrate:  
flame-retardant, Q1, Tr 1
- **French ordinance DEVL1104875A**  
Marking of construction coating products for their emission of volatile pollutants: A+



Application area



For the coating of furniture and interior finishing exposed to high levels of stress, such as tabletops and shelves in the kitchen and living area, bathrooms, offices and in the contract sector, fronts and permanently visible areas, surfaces used on seating furniture and not permanently visible areas. Application areas II to IV in accordance with ÖNORM A 1610-12.

The product is not suitable for surfaces bleached with hydrogen peroxide!

### PROCESSING

Processing instructions



- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least +10 C.
- Due to the dull matt surface effect and the high percentage of matting agents we do not recommend the coating of dark wood or dark stained wood.

- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.
- Please follow our **ARL 131 - Working guidelines for PUR furniture paints.**

### Blending ratio



10 Part(s) by weight Aduro Vitea (2651)  
1 Part(s) by weight PUR-Hardener 8439 (8439000210)

Aduro Vitea (2651) can only be used with a hardener and in the mixing ratio specified. Deviations lead to film and adhesion problems.

### Pot life





8 hour(s)

An extension of the pot life by mixing with freshly hardened paint material is not possible!

Increased temperatures reduce the pot life.

### Application technique



	Airless	Airless air-supported (Airmix®, Aircoat, etc.)	Cup gun
Spraying nozzle Ø (mm)	0,23 - 0,28		1,8
Spraying pressure (bar)	100 - 120	80 - 100	2 - 3
Vaporizer Air (bar)	-	1 - 2	-
Diluent	DD-Verdünner (8519)		
Diluent amount added (%)	0 - 10		10 - 15
Viscosity 4-mm-cup (s)	21		18
Applied quantity per application (g/m <sup>2</sup> )	100 - 130		
Total quantity applied (g/m <sup>2</sup> )	max. 250		

The product is ready to use.

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

For good thorough drying, the recommended application quantities must be adhered to. Excessive layer thicknesses lead to a considerable drying delay!

**Drying times**  
(at 23 °C and 50 % rel. humidity)

Sandable and recoatable	3 h
Manipulable and stackable	12 hour(s)

The figures given above are reference values. Drying depends on the substrate, layer thickness, temperature, air exchange, relative humidity, stacking pressure and stacking conditions.

**Cleaning the working equipment**

8519



8501

With DD-Verdünner 8519 (8519) or Waschverdünner (8501) immediately after use.

**SUBSTRATE****Type of substrate**

Hard and softwood (solid wood-, veneer-, (coated) chipboard-, wood fibre boards)

Please follow our **ARL 130 - Working guidelines for coating various types of wood with solvent-based two-component PUR paints.**

**Substrate property**

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

**Substrate preparation**

**Hardwoods:** Wood sanding Grit size 150 – 180

**Softwoods:** Wood sanding Grit size 120 - 150

**COATING SYSTEM****Primer coat**

1 x Aduro Vitea (2651)

**Intermediate sanding**

Sand the primed surface with grit size 280 – 320.

Avoid sanding straight through!

Intermediate sanding must be carried out immediately before the subsequent coating is applied in order to ensure good intermediate adhesion!

**Topcoat**

1 x Aduro Vitea (2651)

**CLEANING AND MAINTENANCE****Cleaning and Maintenance**

Cleaning with Clean-Möbelreiniger (7202) and care with Clean-Möbelpflege Plus (7222).

**ORDERING INFORMATION****Size of trading unit**

4 kg, 20 kg

**Supplementary products**

Clean-Möbelpflege Plus (7222)  
Clean-Möbelreiniger (7202)  
DD-Verdünner 8519 (8519)  
PUR-Hardener 8439 (8439)  
Waschverdünner 8501 (8501)

Please refer to the corresponding technical data sheets of the products.

## FURTHER DETAILS

### Durability / storage



Min. 1 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

### Technical specifications

Delivery viscosity: 23 second – 26 second according to DIN 53211  
(4 mm measuring cup, 20 °C)

### Safety information



The product is only suitable for the industrial and professional use.

The inhalation of paint aerosols during spray application must generally be avoided. This is ensured by the proper use of a respirator (combination filter A2/P2).

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at [www.adler-lacke.com](http://www.adler-lacke.com).