

Legno Zirbenöl

7028

Oil with the natural scent of Swiss pine for furniture and interior finishing for DIY and trade

PRODUCT DESCRIPTION

General

Easy to use, fast-drying oil, specially developed for the treatment of Swiss pine timber. The product has been formulated largely with renewable raw materials and natural Swiss pine oil. The natural characteristics of the Swiss pine are retained.
Very good penetration capacity, excellent accentuation of the wood grain, a pleasant feel, very good filling performance, very good water resistance. Antistatic.
Hardening is achieved by absorption of oxygen from the atmosphere (oxidative drying).

Special properties and standards



- **DIN 53160-1 and DIN 53160-2**
Perspiration and saliva-proof properties



- **ÖNORM EN 71-3**
Safety of toys; migration of certain elements (free of heavy metals)



- **French ordinance DEVL1104875A**
Marking of construction coating products for their emission of volatile pollutants: A+

Application area



For the surface treatment of furniture and interior finishing surfaces that are subject to a normal level of wear, e.g. bedroom and living room fittings.

Substances contained

Modified vegetable oils, waxes, silicic acid, mild-odour solvents, lead-free and cobalt-free drying agents.

Natural Swiss stone pine oil

PROCESSING

Processing instructions



- Please stir the product before use.
- The product is ready to use.
- The temperature of the product and object, and the room temperature must be at least +10 C.

1-1 IMC 7028 | 04/25 | replaces 1-0

ADLER-Werk Lackfabrik, A-6130 Schwaz

Fon: +43/5242/6922-190, Fax: +43/5242/6922-309, Mail: technical-support@adler-lacke.com

Our instructions are based on the current state of knowledge and are intended to advise the buyer/user to the best of our knowledge, but must be individually adapted to the areas of application and processing conditions. The buyer/user is responsible for deciding on the suitability and use of the supplied product, which is why we recommend that a sample be produced to check the suitability of the product. In all other respects, our General Terms and Conditions of Sale apply. All previous data sheets lose their validity with this edition. We reserve the right to make changes to container sizes, color shades and available gloss levels.

- The optimal conditions for use are between 20 - 25 °C with a relative atmospheric humidity between 40 - 60 %.
- Apply the product and leave a short time to take effect and then carefully wipe of the excess with a cotton cloth or pack of gauze in the direction of the fibre. The formation of a film must be avoided at all costs!
- Apply a maximum of one thin coat of this product to the inner surfaces of furniture and cabinets on account of possible odours.
- **Attention:** Care should be taken to sand the wood uniformly and to apply the product evenly!
- **Important:** With hardwoods and tropical woods that are rich in active substances, we strongly recommend doing a test treatment with Legno Zirbenöl (7028) before proceeding.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.
- Please read and take note of our working guidelines **ARL 013 – Safety measures required for the use of oils and waxes that dry by oxidation** and **ARL 160 – Working guidelines for oils and waxes**.

Application technique



	Cup gun	Brushing	Rolling	Wiping
Spraying nozzle Ø (mm)	1,5		-	
Spraying pressure (bar)	2 - 3		-	
Yield per application (m ² /l)		15 - 30		
Applied quantity per application (g/m ²)	30 - 50		-	

The stated yield includes spray loss.

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times

(at 23 °C and 50 % rel. humidity)



Follow-up treatment	4 h
Thoroughly dried	7 day(s)

The figures given above are reference values. Drying depends on the substrate, layer thickness, temperature, air exchange, relative humidity, stacking pressure and stacking conditions.

To ensure perfect drying, good room ventilation must be provided. Low ventilation, e.g. from dense stacking, delays drying.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

On types of woods rich in extracts (such as oak, iroko), drying may be delayed.

Cleaning the working equipment



With Legno-Reiniger (7003) or Adlerol-Terpentinölersatz (7231) immediately after use.

SUBSTRATE

Type of substrate	Fine-pored and coarse-pored hardwoods and softwoods. Particularly suitable for Swiss stone pine
Substrate property	The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.
Wood moisture	Hardwoods: $12 \pm 2 \%$ Softwoods: $15 \pm 2 \%$
Substrate preparation	Sand with grit size 180 - 240 and clean. Remove sanding dust.



PROCESSING STEPS

Basic treatment	1 x Legno Zirbenöl (7028)
Intermediate sanding	Slight smooth sanding: Grit size 280 – 360 Remove sanding dust.
Final treatment	1 x Legno Zirbenöl (7028)



CLEANING AND MAINTENANCE

Cleaning	Clean with water, Clean-Möbelreiniger (7202) or a mild household detergent. Use Legno Reiniger (7003) for greasy stains. Cleaning must be carried out at the earliest 14 days after application of the oil/wax/hard wax oil. Abrasive cleaning agents should not be used.
Maintenance	For freshening up and after-care apply 1 x Legno Zirbenöl (7028) and wipe away the excess.

ORDERING INFORMATION

Size of trading unit	750 ml, 2.5 l
Colour shades	Standard colour(s): Farblos (7028000200) The final colour achieved is very dependant on the inherent colour of the wood and the quantity of the product that is applied.
Supplementary products	Adlerol-Terpentinölersatz (7231) Clean-Möbelreiniger (7202) Legno Reiniger (7003) Please refer to the corresponding technical data sheets of the products.

FURTHER DETAILS

Durability / storage



Min. 1 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

We recommend to transfer the contents of open containers to smaller ones in order to prevent gelling / skin formation.

Giscode

Ö100

Safety information



The inhalation of paint aerosols during spray application must generally be avoided. This is ensured by the proper use of a respirator (combination filter A2/P2).

When sanding, use at least a P2 dust filter as personal safety equipment to protect against abrasive and wood dust.

Using the product in spraying booths, which are contaminated with nitrocellulose-containing spray dust, is prohibited owing to the risk of self-ignition!

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.